

# Agilus30

## Polyjet Rubber-Like Material

[Agilus30™](#) is a superior Rubber-like [PolyJet™](#) photopolymer family ideal for advanced design verification and [rapid prototyping](#). Get more durable, tear-resistant prototypes that can stand up to repeated flexing and bending. With a Shore A value of 30 in clear, black and white, Agilus30 accurately simulates the look, feel and function of Rubber-like products. 3D print rubber surrounds, overmolds, soft-touch coatings, living hinges, jigs and fixtures, wearables, grips and seals with improved surface texture.

Mechanical Properties	Test Method	Value	
		Black / Translucent	White
Tensile Strength	ASTM D-412	2.4 – 3.1 MPa (348 – 450 psi)	2.1-2.6 MPa (305 – 377 psi)
Elongation at Break	ASTM D-412	220 – 270%	185 – 230%
Compressive Set	ASTM D-395	6 – 7%	6 – 7%
Tensile Tear Resistance	ASTM D-624	4 – 7 Kg/cm (22 – 39 lb/in)	4 – 7 Kg/cm (22 – 39 lb/in)

Other	Test Method	Value	
		Black / Translucent	White
Shore Hardness	ASTM D-2240	30 – 35 Scale A	30 – 40 Scale A
Polymerized Density	ASTM D-792	1.14 – 1.15 g/cm <sup>3</sup>	1.14 – 1.15 g/cm <sup>3</sup>

System Availability	Layer Thickness Capability	Support Structure	Available Color
<a href="#">Objet260/350/500</a> <a href="#">Connex1/2/3™</a> <a href="#">Stratasys J735™/</a> <a href="#">Stratasys J750™</a>	High Speed mode: 30 microns (0.0012 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White <sup>1</sup>

<sup>1</sup> Stratasys J735 and Stratasys J750 only.

### Stratasys Headquarters

7665 Commerce Way,  
Eden Prairie, MN 55344  
+1 800 801 6491 (US Toll Free)  
+1 952 937-3000 (Intl)  
+1 952 937-0070 (Fax)

stratasys.com  
ISO 9001:2008 Certified

1 Holtzman St., Science Park,  
PO Box 2496  
Rehovot 76124, Israel  
+972 74 745 4000  
+972 74 745 5000 (Fax)